Fast Setting Cement Self-Priming Cement BLUE MONSTER

1-Step CPVC Cement







Medium Body - Low VOC Cement for copper tube-size pipe and fittings through 2" diameter

Blue Monster 1-Step CPVC cement is a self-priming pipe glue that requires no additional primer. This cement is a medium bodied, fast-setting CPVC cement for use on copper tube size (CTS) CPVC pipe and fittings up to 2" diameter with interference fit.

Blue Monster 1-Step CPVC cement is formulated for use as a 1-step cement where the use of a primer is not required where local codes permit. This cement meets the low-VOC emission limit as outlined by South Coast Air Quality Management District (SCAQMD).

Blue Monster 1-Step CPVC cement is designed for use in residential, commercial and industrial cold and hot water CPVC piping systems up to 180°F (82°C).

This cement is listed by NSF International for compliance with ASTM F 493, the Uniform Plumbing Code, NSF/ANSI Standard 14, NSF/ANSI Standard 61 for use on potable water, drain, waste, vent and sewer applications (pw-G-dwv-sw).

For Material Safety Data Sheets, contact Mill-Rose or download directly from the Mill-Rose Clean-Fit website.

- No Primer Required*
- Fast Set, One-Step Cement
- Use in Hot or Cold Piping Systems
- Residential, Commercial & Industrial Applications
- Allows for Immediate Pressure Testing
- Eco-Friendly Low VOC

Cat #	Size	Case Pack	Weight
76041	1/4 pint / 4 fl. oz. / 118 ml	24	10 lbs.
76043	1/2 pint / 8 fl. oz. / 237 ml	24	16 lbs.
76045	1 pint / 16 fl. oz. / 473 ml	12	15 lbs.
76047	1 quart / 32 fl. oz. / 95 ml	12	28 lbs.

NSF.

pw/dwv/sw Standard 14 Standard 61 *Use without primer where acceptable by local code.



Fast Setting Self-Priming Cement

1-Step CPVC Cement







PRODUCT SPECIFICATIONS			
Pipe type	All rigid CPVC, copper tube size		
Cement Uses	For potable water to 180°F (82°C). Suitable for residential plumbing and industrial systems.		
Maximum Diameter	2 inches (63mm)		
Color	Yellow		
Relative Set Time	Fast Set		
Body	Medium Bodied		
Performance Specification	ASTM F493 & D2846 SCAQMD Rule 1168/316A NSF/ANSI Standard 14 and 61 IAPMO Uniform Plumbing Code CSA standard B137.6		
Brookfield Viscosity	Minimum 500 cps		
Specific Gravity	0.977 ± 0.04		

SPECIAL PRECAUTION

Blue Monster solvent cements must never be used in plastic piping system using or being tested by compressed air or gases; including air-over-water booster. Do not use in conjunction with flue gas ventilation systems. Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems The introduction of granules or pellets of calcium hypochlorite with solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system – this solution will be nonvolatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

This product is intended for use by skilled individuals at their own risk. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Detailed directions on making solvent cemented joints are printed on the container label. It is highly recommended that the installer review the instructions supplied by the pipe and fitting manufacturer.

Refer to the current Safety Data Sheet for additional safety precautions, first-aid, storage, handling, transportation and disposal information.



WARNING: Cancer -www.P65Warnings.ca.gov



VOC Emissions

Shelf Life



377 g/L

2 Years





